

# KOPR-KOTE®

## TOOL JOINT & DRILL COLLAR COMPOUND



OILFIELD

### DESCRIPTION

**KOPR-KOTE®** drill collar and tool joint compound is a premium-quality, unleaded compound containing copper flake, graphite, and other natural extreme pressure and anti-wear additives. **KOPR-KOTE's** solids package is formulated to prevent excessive circumferential makeup by increasing the coefficient of friction under compressive forces. As stress levels rise above 50% of yield, the friction factor increases, limiting downhole makeup. Full hydraulic joint efficiency is maintained allowing joint shoulder faces to mate completely without standoff or deformation. **For invert or high-pH muds, use Jet-Lube EXTREME™. For wedge thread connections, use NCS-30™ ECF for best thread-wear protection.**

- **Not classified as marine pollutant - DOT Approval CA2004080025**
- Contains no lead or zinc.
- Extreme-pressure additives provide additional protection against seizing and galling and allow consistent make-up.
- Aluminum-complex grease base protects against rust and corrosion.
- Sticks to wet joints.
- Unequaled resistance to makeup downhole.
- Available in Arctic, Thermal, and Specialty grades.
- Approved by NAM/Shell for under-balanced drilling applications.

For optimum performance on API drill string connections, **KOPR-KOTE** should be utilized with the torque charts in API RP7G or by contacting the drill pipe and connection manufacturer.

Premium drill string connections such as HI-TORQUE® (HT), eXtreme® Torque (XT®), and XT-M™ connections, etc., utilize make-up torques based upon thread compound friction factors of 1.0. Therefore, use the torque provided by the premium connection manufacturer. Adjusting make-up torque based on thread compound friction factor may still be advised.

**SERVICE RATING:**  
0°F (-18°C) TO 450° (232°C)

### PRODUCT CHARACTERISTICS

Thickener	Aluminum Complex
Fluid Type	Petroleum
Dropping Point	450°F (232°C)
(ASTM D-2265)	
Specific Gravity	1.15
Density (lb/gal)	9.6
Oil Separation (ASTM D-6184)	<3.0
Wt. % Loss @ 212°F (100°C)	
Flash Point (ASTM D-92)	>430°F (221°C)
NLGI Grade	1
Penetration @ 77°F	310 - 330
(ASTM D-217)	
Copper Strip Corrosion	1A, typical
(ASTM D-4048)	
4-Ball (ASTM D-2596)	
Weld Point, kgf	800, typical
Friction Factor*	1.0
(Relative to API RP 7G)	

\* Many factors such as pipe size, thread geometry, drilling mud contamination, etc. affect the friction factor. This is a relative number and in all applications experience and prior knowledge should be used to adjust make-up torque accordingly. Contact your drill pipe manufacturer for torque and friction-related specifications.

### PACKAGING

Part #	Container Size	Container
10123	1 gal/4L	Pail
10115	5 gal/20L	Pail

### LIMITED WARRANTY

Jet-Lube, Inc. makes the Limited Express Warranty that at the date of delivery, this product shall be free from defects in Jet-Lube, Inc. materials and workmanship.

This Limited Express Warranty is expressly in lieu of any other express or implied warranties, including any implied warranty of merchantability or fitness for a particular purpose, and of any other obligation on the part of Jet-Lube, Inc.

The sole remedy for breach of the Limited Express Warranty shall be the refund of the purchase price. All other liability is negated and disclaimed, and Jet-Lube, Inc. shall not be liable for incidental or consequential damages.



**Distributed by**

**1300-00-XTEX**  
**sales@xtex.com.au**  
**www.xtex.com.au**